

CUT IN REGLET 1" DEEP MIN. PRE-SATURATE EDGE OF JM PMMA SCRIM AND TUCK INTO REGLET. (THIS TECHNIQUE IS OPTIONAL AND IS FOR CONC./MASONRY ONLY. TYPICALLY TERMINATE JM PMMA

APPLY APPROPRIATE SEALANT CONTINUOUS ALONG TOP OF FLASHING (FOR REGLET INSTALLATION ONLY)

ROOF LADDER ANCHORED TO **BUILDING (BY OTHERS)**

THOROUGHLY CLEAN STEEL AND APPLY JM PMMA METAL PRIMER PRIOR TO INSTALLATION OF JM PMMA MEMBRANE FLASHING

LADDER SUPPORT ANGLES WRAPPED WITH JM PMMA MEMBRANE AND EXTENDED ONTO ROOF MEMBRANE

PREPARE, LEVEL & PATCH SUBSTRATE WITH JM PMMA REPAIR PASTE AFTER PRIMING & PRIOR TO INSTALLATION OF JM PMMA MEMBRANE

FLASHING EXTENDED 4" MIN. HORIZONTALLY ONTO PREPARED AND PRIMED SUBSTRATE

ENSURE ALL MEMBRANE TERMINATIONS ARE ENCAPSULATED IN JM PMMA RESIN

ENSURE FULL RESIN SATURATION OF JM PMMA SCRIM AND CONTACT WITH SUBSTRATE

JM PMMA FIELD MEMBRANE

mm) MIN 0 0 (102 4" (102 mm) MIN

LADDER ELEVATION

NOTES:

- 1. REFER TO JOHNS MANVILLE WEBSITE (www.jm.com) FOR MOST UP-TO-DATE INFORMATION.
- 2. PLEASE SEE JM PMMA FLASHING SPECIFICATIONS FOR A FULL DESCRIPTION OF INSTALLATION INSTRUCTIONS AND REQUIREMENTS WHICH ARE CONSIDERED A PART OF THIS DETAIL.
- 3. ANY CARPENTRY OR METAL WORK SHOULD BE DESIGNED AND CONSTRUCTED IN ACCORDANCE WITH LOCAL CODE REQUIREMENTS AND/OR PROJECT SPECIFICATIONS. THESE COMPONENTS SHOULD BE REVIEWED AND APPROVED BY A LICENSED DESIGN PROFESSIONAL.
- 4. JM PMMA MEMBRANE FLASHING CONSISTS OF JM PMMA FLASHING RESIN, JM PMMA SCRIM, JM PMMA FLASHING RESIN. USE THE APPROPRIATE JM PMMA PRIMER DEPENDING ON TYPE OF SUBSTRATE.
- 5. ALL SEALANTS / CAULKING SHALL BE PERIODICALLY INSPECTED AND MAINTAINED BY THE BUILDING OWNER THROUGHOUT THE LIFE OF THE ROOF.

WALL MOUNTED LADDER BASE FLASHING

DRAWING NO. FLASHING WALL

MEMBRANE TYPE:	ISSUE DATE
JM PMMA	04-10-24
MAXIMUM GUARANTEE TERM:	SCALE
20 YEAR	N.T.S

Johns Manville is a manufacturer of commercial roofing products and offers this general conceptual information to you as a courtesy for general educational purposes only. This complimentary iniormation to you as a coursely or general equations purposes only. This complimination assistance is not to be either used or reflied upon by anyone as a substitute for professional engineering design and documentation required by any building code, contract, or applicable law. By accepting the general conceptual information, you agree it does not constitute any representations, endorsements of, or an assumption by Johns Manville of any duty or liability for either the adequacy of the design of a building, any of its components or the sufficiency of any construction.

